Weierstraß-Institut für Angewandte Analysis und Stochastik

Leibniz-Institut im Forschungsverbund Berlin e. V.

Preprint

ISSN 2198-5855

Counterion-controlled phase equilibria in a charge-regulated polymer solution

Giulia L. Celora¹, Ralf Blossey², Andreas Münch³, Barbara Wagner⁴

submitted: July 10, 2023

 Department of Mathematics University College London
 25 Gordon Street London, WC1H 0AY, UK
 E-Mail: g.celora@ucl.ac.uk ² Unité de Glycobiologie Structurale et Fonctionnelle (UGSF) CNRS UMR8576 University of Lille F-59000 Lille, France E-Mail: ralf.blossey@univ-lille.fr

³ Mathematical Institute University of Oxford Woodstock Road Oxford, OX2 6GG, UK Email: muench@maths.ox.ac.uk

 ⁴ Weierstrass Institute Mohrenstr. 39
 10117 Berlin Germany
 E-Mail: barbara.wagner@wias-berlin.de

> No. 3031 Berlin 2023



2020 Mathematics Subject Classification. 34C23, 41A60, 80A30.

Key words and phrases. Liquid-liquid phase separation, polymer solution, charge regulation.

GLC is supported by the UK Engineering and Physical Sciences Research Council (EPSRC), grant number EP/W524335/1.

Edited by Weierstraß-Institut für Angewandte Analysis und Stochastik (WIAS) Leibniz-Institut im Forschungsverbund Berlin e. V. Mohrenstraße 39 10117 Berlin Germany

Fax:+493020372-303E-Mail:preprint@wias-berlin.deWorld Wide Web:http://www.wias-berlin.de/

Counterion-controlled phase equilibria in a charge-regulated polymer solution

Giulia L. Celora, Ralf Blossey, Andreas Münch, Barbara Wagner

Abstract

We study phase equilibria in a minimal model of charge-regulated polymer solutions. Our model consists of a single polymer species whose charge state arises from protonation-deprotonation processes in the presence of a dissolved acid, whose anions serve as screening counterions. We explicitly account for variability in the polymers' charge states. Homogeneous equilibria in this model system are characterised by the total concentration of polymers, the concentration of counter-ions and the charge distributions of polymers which can be computed with the help of analytical approximations. We use these analytical results to characterise how parameter values and solution acidity influence equilibrium charge distributions and identify for which regimes unimodal and multi-modal charge distributions arise. We then study the interplay between charge regulation, solution acidity and phase separation. We find that charge regulation has a significant impact on polymer solubility and allows for non-linear responses to the solution acidity: re-entrant phase behaviour is possible in response to increasing solution acidity. Moreover, we show that phase separation can yield to the coexistence of local environments characterised by different charge distributions and mixture compositions.

1 Introduction

Solutions with charged polymers can demix into polymer-rich phases, also known as condensates. When the condensed phase remains liquid, the process yielding to demixing is known as liquid-liquid phase separation or coacervation. In recent years, the understanding of liquid-liquid phase separation (LLPS) has gained enormous interest because of its putative role in the assembly of macromolecules (mostly proteins and nucleic acids) into membrane-less organelles (also known as biomolecular condensates) in cells [25, 34]. While polymer physics theories have elucidated several aspects of phase separation in solution, it is not yet fully understood how different molecular mechanisms affect the formation, regulation and properties of biomolecular condensates in cells [34]. Challenges relate to the complexity of proteins, that are large heteropolymeric polyelectrolytes, and of the cellular environment which is maintained out of equilibrium and can itself modulate proteins properties and coacervation [34].

Grounded in the seminal work by Flory and Huggins (FH) on phase separation in polymer solutions, the balance between enthalpic and entropic interactions is considered to be the driving force of LLPS. Based on the simplifying assumption of polymers consisting on chemically identical units, Flory and Huggins derived a mean-field model for phase separation in two-components mixtures. Such a model has proven a useful phenomenological model also to study phase-separation in protein solutions. However, its has limited predictive power, as it misses details on the nature of the intermolecular interactions that contribute to the enthalpic part of the free energy [5, 34].

A feature common to proteins is the presence of ionizable groups, that contribute to the electrostatic interactions between proteins [28]. Models of polyelectrolyte coacervation are commonly employed to

study the role of electrostatic interactions as well as salt in LLPS. The early key paper in the field of polyelectrolyte complexation (also called complex coacervation) remains the work by Voorn and Overbeck from 1957 [22]. Extensions of these classical theories that capture the sequence-dependence of LLPS driven by proteins with intrinsically disordered domains, as first demonstrated in [20], have employed mean-field theories of polyampholytes as underlying models of proteins. They include the Random Phase Approximation [16, 17], as well as Field Theoretic Simulations [38] for the residue specific electrostatic interactions; recent reviews in the modern context are [4, 30, 31, 26].

A limitation of all these approaches is that they assume the charge state on the polymers, such as polyelectrolytes or polyampholytes, to be fixed; in contrast, as shown earlier on by the work of Linderstrøm-Lang [8], the charge state of proteins is in fact regulated by the local environment, such as pH conditions, as well as by interactions between ionizable groups themselves [23, 32]. A key process in this context is charge regulation of the polymers or, more generally, chargeable macromolecules in the cellular context [2, 3]. The charge regulation process is best explained in its most elementary variant which consists in the binding and unbinding of protons, H^+ , from the water solvent. It is immediately clear that this protonation-deprotonation process goes in hand-in-hand with the change of solution pH [1]. More involved charge regulation processes are obviously present, e.g. in the binding of dissolved salts in solutions. The effect of charge regulation processes has on phase equilibria has been addressed in several recent papers [18, 11, 27, 6, 19, 39, 35]. However, even in simple model systems, the complexity of the interactions yields phase behaviours in multi-parameter spaces which are nontrivial to analyse. This is particularly true due to the highly non-linear free energy terms associated with electrostatic correlation effects, a key feature of liquid-liquid phase separating systems and of fundamental relevance in cell biology [14, 24, 29, 10, 36, 37, 13].

In cell biology, the relation between the phase diagram on the one hand and the charge states of the macromolecules on the other [9] is of particular interest. In this paper, we address this issue on the basis of a 'minimal' model which has essentially two ingredients: a basic formulation of the Voorn-Overbeek theory and the charge regulation mechanism, for which we keep track of the charge state on the polymers following the charge distribution approach developed in [3]. Another key novelty that distinguishes our work from previous studies on phase separation and charge regulation processes [18, 39] is that we consider the protonation-deprotonation equilibria in solution in the presence of a dissociated acid. The concentration of the counterions due to acid dissociation will turn out to be a key control parameter in our model system. In this way, we are capable to gain insights into the coupling between charge regulation, acidity and phase separation, by linking topological changes in the coexistence curves as well as the related changes in the charge distributions on the polymers.

Our paper is organised as follows. In 2 we introduce our model for the polymer-solvent mixture. Section III covers the results we have obtained from its analysis. Section III A describes its homogeneous equilibrium states, with a focus on how the composition of the mixture affects the polymer charge. Section III B then discusses phase equilibria in our system. Finally, in Section III C we show how phase separation process itself regulates the charge state of the polymers by controlling the local environmental conditions – here acidity. Section IV concludes and provides an outlook to further studies; in particular, we discuss the putative relevance of our results for LLPS in biological systems. Section V contains the Appendices in which the technical results employed in the paper are derived.

2 A model for a polymer-solvent mixture

Components of the mixture. The building blocks of our model and the charge regulation mechanism



Figure 1: **Mixture components.** Schematic representation of the mixture components: water (H₂O), positive ions (H⁺), counterions and polymers chains which consists of N monomers. Of the N monomers polymers are made of, Z have a binding site for H⁺ ions. The binding sites can either exist in a charged or uncharged state; as a result, polymers in the mixture can be in any charge state $z \in \{0, \ldots, Z\}$. Schematic illustrating charge regulation mechanisms: (b) for an individual monomer; (c) for an entire polymer chain.

it entails are illustrated in Figure 1, respectively. We consider chargeable polymers solvated in water, H₂O, and a strong acid; here as an example, we consider hydrochloric acid, HCl. Therefore, in solution, we encounter the dissociated ionic species: Cl⁻ and hydronium ions H₃O⁺. The polymers are considered as monodisperse with $N \gg 1$ monomers, of which only a subset of Z monomers carries a protonation site, which can either be positively-charged (bound state) or neutral (unbound state). We assume that H₃O⁺, Cl⁻ and the monomers making up the polymer have the same molecular volume as water, ν , so that the polymers have the molecular volume $\nu_M = N\nu \gg \nu$. As in [3], we assume that polymers with different charge states, $z \in \{0, \ldots, Z\}$, coexist in the mixture; as a result, we have effectively Z + 1 different polymer species in solution. Together with water, chloride and hydronium ions this gives a total of Z + 4 species that we take into account in our mixture. For each species, we denote by ϕ_{ω} the volume fraction, with $\omega = (s, +, \ell, z) =$ (solvent, hydronium ions, chloride ions, charged polymer). The volume fractions must satisfy a no-void condition, which guarantees that at any location space is fully occupied by the mixture:

$$\phi_s + \phi_+ + \phi_\ell + \phi_M = 1,\tag{1}$$

where

$$\phi_M = \sum_{z=0}^Z \phi_z.$$
 (2)

Furthermore, we assume that our solution is electroneutral so that the net charge density of the mixture has to be zero,

$$\phi_{+} - \phi_{\ell} + \sum_{z=1}^{Z} \frac{z}{N} \phi_{z} = 0.$$
(3)

The free energy density of a homogeneous mixture. We assume that the mixture is incompressible and kept at a constant temperature T, and describe it by a Helmholtz free energy density f which consists of three contributions, similar to [39],

$$f = f_1 + f_2 + f_3 \,. \tag{4}$$

The chemical potentials of the different species in the mixture are then expressed in terms of derivatives of the Helmholtz free energy density f with respect to ϕ_{ω} ; these conditions are given in detail in Appendix A. The first contribution f_1 in (4) is the standard Flory-Huggins free energy capturing the entropic contributions and an interaction term of water and the solvated polymer

$$\frac{f_1\nu}{k_BT} = \sum_{k \in \{+,\ell,s\}} \phi_k \ln(\phi_k) + \sum_{z=0}^Z \frac{\phi_z}{N} \ln(\phi_z) + \chi \sum_{z=0}^Z \phi_s \phi_z.$$
 (5)

For simplicity, we assume the interaction parameter χ to be independent of the charge on the polymers. The second contribution, f_2 , in (4) is due to charge regulation and given by

$$\frac{f_2}{k_B T} = \frac{1}{\nu_M} \sum_{z=0}^Z u_z \phi_z.$$
 (6)

where u_z is the difference in the internal free energy (non-dimensionalised by k_BT) of a polymer with charge z and a neutral one. By neglecting chain connectivity of the polymers, we can see the charged polymer as a mixture of an uncharged polymer and z positive fixed charges. Following [3], we specify u_z as

$$u_z = \alpha z + \frac{\eta z^2}{2Z} - \ln\left[\binom{Z}{z}\right].$$
(7)

In (7), the first contribution represents the energy gain (again non-dimensionalised by $k_B T$) from occupying an additional site on the polymer by an H^+ ion. The second term represents an additional contribution from short-range interactions between occupied binding sites whose strength is controlled by the parameter η . Finally, we have to include the internal entropy to account for the different ways to arrange fixed charges on the binding sites.

The last term f_3 is the Debye-Hückel term, similar to [39], which like our reasoning for f_2 assumes that the charges on the monomers of the polymers can be treated as free ions,

$$\frac{f_3}{k_B T} = -\frac{1}{4\pi\nu} \left(\ln(1+\kappa) - \kappa + \frac{\kappa^2}{2} \right),\tag{8}$$

where

$$\kappa^2 = \lambda \left(\phi_+ + \phi_\ell + \frac{\nu}{\nu_M} \sum_{z=1}^Z z \phi_z \right) = 2\lambda \phi_\ell.$$

Note that the term κ^2 depends on the sum of all charged molecules multiplied by their valency (as in Eq. (6) in [39]). The simplified expression Eq. (9) is obtained by applying (3). In Eq. (9) the parameter $\lambda = 4\pi \ell_B / a_w$, where ℓ_B is the Bjerrum length in water and $a_w = \nu^{1/3}$ is the size of the species in the solution. More realistic models that include polymer connectivity have, e.g., been discussed in [24]. However, these include information on the specific location of the charges along the polymer chains.

The charge regulation process. As mentioned in the introduction, models of polymer coacervation commonly assume the charge state on the polymer phase to be fixed. In our framework, this corresponds to assuming that all protonation sites on the polymer are occupied, *i.e.*, imposing in Equations (5)—(9) $\phi_z = 0$ for all $z = \{0, \ldots, Z - 1\}$. We instead assume that charges can reversibly bind to protonation sites according to the reaction

$$\mathcal{M}_z + \mathrm{H}_3\mathrm{O}^+ \rightleftharpoons \mathcal{M}_{z+1} + \mathrm{H}_2\mathrm{O}, \quad 0 \le z \le Z - 1,$$

where M_z represents the polymer with z charges. Then, the charge states of polymers in solution is determined by imposing chemical equilibrium, instead of being prescribed *a priori*.

Making use of the definition of the Helmholtz free energy (see A.1) we have that the change in the free energy for each chemical reaction ($M_{z-1} + H_3O^+ \implies M_z + H_2O$) occurring in the mixture is given by

$$F(T, V, N_s + 1, N_+ - 1, \dots, N_{z-1} - 1, N_z + 1, \dots) - F(T, V, N_s, N_+, \dots, N_{z-1}, N_z, \dots)$$

= $\mu_s + \mu_z - \mu_+ - \mu_{z-1}, \quad 0 < z \le Z.$ (9)

At chemical equilibrium, Eq. (9) must be zero – *i.e.*, the difference in chemical potential of products and reactant of each chemical reaction must be zero. Manipulating Eq. (9) we can express μ_z in terms of the chemical potential of the counterions, solvent and uncharged polymers:

$$\mu_z = \mu_{z-1} + \mu_+ - \mu_s, \quad z = 1, \dots, Z.$$
(10)

10 can be viewed as an iterative discrete map that, given μ_0 , defines the chemical potential of all charged polymers in terms of μ_+ and μ_s ,

$$\mu_z = \mu_0 + z(\mu_+ - \mu_s), \quad z = 1, \dots, Z.$$
 (11)

Using the explicit form of the chemical potential (31) in (11) we arrive at

$$u_{z} + \ln(\phi_{z}) = -z\chi\phi_{M} + \ln\phi_{0} + z\ln\left(\frac{\phi_{+}}{\phi_{s}}\right),$$

$$z = 0, \dots, Z,$$
 (12)

where u_z is defined by 7 and

$$\phi_0 = \phi_M - \sum_{z=1}^{Z} \phi_z.$$
 (13)

Taking the exponential of both sides of (12), we obtain a system of Z + 1 linear algebraic equations for the volume fractions ϕ_z ; this can be solved explicitly to obtain an expression for ϕ_z , $z = 0, \ldots, Z$,

$$\phi_z = \phi_M \pi_z \tag{14}$$

with

$$\pi_z = \mathcal{A}e^{-u_z + (\ln \phi_+ - \ln \phi_s - \chi \phi_M)z} \tag{15}$$

where

$$\mathcal{A}^{-1} = \sum_{z=0}^{Z} e^{-u_z + (\ln \phi_+ - \ln \phi_s - \chi \phi_M)z}.$$
 (16)

The terms π_z indicate the fraction of the total number of polymers in the charged state z as a function of the mixture composition. By definition, their sum must be unity, $\sum_{z=0}^{Z} \pi_z = 1$. Inspecting (15), we find that π_z can be rewritten in terms of an effective charge regulation free energy,

$$\pi_z = \mathcal{A} \exp\left(-u_z^{\text{eff}}\right),\tag{17}$$

where

$$u_{z}^{\text{eff}} = \alpha_{\text{eff}} z + \frac{\eta z^{2}}{2Z} - \ln \left[\begin{pmatrix} Z \\ z \end{pmatrix} \right],$$
(18a)

with
$$\alpha_{\text{eff}} = \alpha + \ln(\phi_s) - \ln(\phi_+) + \chi \phi_M$$
. (18b)

The comparison of Eq. (18a) to the definition of u_z (see Eq. (7)), shows that, in our system, the local composition of the mixture affects the charge regulation process by controlling the energy associated with the protonation/deprotonation of a single binding site. Note the introduction of an effective parameter α_{eff} that includes a composition-dependent correction to the 'bare' linear term in u_z . As in [3], we find that the ion concentration in solution, ϕ_+/ϕ_s , affects the effective binding energy. Furthermore, by introducing the Flory-Huggins term in the free-energy, we have that the polymer concentration, ϕ_M , itself affects the binding of ions in solution (see the last term in Eq. (18b)).

Using (15) to eliminate ϕ_z (z = 0, ..., Z) from the definition of free energy density (see (4)-(8)) we obtain the expression for the free energy for an ionic solution with charge regulating polymers

$$\frac{\nu f_{c_{\mathsf{R}}}}{k_B T} = \phi_{+} \ln \left[\phi_{+}\right] + \phi_{\ell} \ln \left[\phi_{\ell}\right] + \phi_{s} \ln[\phi_{s}] + \chi \phi_{M} \phi_{s}$$

$$+ \frac{\phi_{M} \nu}{\nu_{M}} \left(\ln \phi_{M} + \ln \left[\mathcal{A}\right]\right)$$

$$+ \frac{\mathcal{Q} \phi_{M} \nu}{\nu_{M}} \left(\ln \phi_{+} - \ln \phi_{s} - \chi \phi_{M}\right)$$

$$- \frac{1}{4\pi} \left(\ln(1+\kappa) + \frac{\kappa(\kappa-2)}{2}\right)$$
(19)

where $\kappa = \sqrt{2\lambda\phi_{\ell}}$ and we have introduced the variable Q that represents the mean charge of the polymer phase $Q = \sum_{z=0}^{Z} z\pi_z$ While we have defined the free energy in terms of the variables ϕ_s , ϕ_+ , ϕ_M and ϕ_ℓ , the degrees of freedom of the model can be reduced to only two by observing the two constraints (no-void and electro-neutrality) formulated in (1) and (3), that is $\phi_s = 1 - \phi_M - \phi_\ell - \phi_+$, and $\phi_+ = -\frac{\phi_M}{N}Q + \phi_\ell$.

These determine ϕ_s and ϕ_+ in terms of ϕ_M and ϕ_ℓ , albeit, in the case of ϕ_+ , only implicitly.

3 Results

In the current work, we focus on the interplay between charge regulation processes and phase separation. Our analysis highlights the key role of parameter η in the equilibrium properties of the system. We, therefore, consider it as a free parameter while fixing the others. Based on previous works, we set $\lambda = 26.68$ [39] and $\nu \approx 3.1 \times 10^{-23}$ ml [39]. The number of monomers in the protein is set to N = 100; of these, we assume that Z = 20 have a H⁺ binding site. We set $\alpha = -6.5$ so that it is energetically favourable for an individual binding site to be occupied (see 1b). The temperature is fixed to T = 298 K and the Flory parameter to $\chi = 0.95$; the latter value is chosen so that phase separation is observed – even when considering a neutral polymer (see 3.2.2).



Figure 2: **Composition-dependent charged states.** Parameter diagram for the charge distribution of homogeneous states as a function of α_{eff} and η , obtained by computing the extrema of \tilde{u}_{eff} (see (20)). The insets show \tilde{u}_{eff} for specific values of α_{eff} and η . In the green region \tilde{u}_{eff} has two minima; outside this region a unique minimum exists and its position is indicated by the colorbar above the diagram. The change of the effective binding energy parameter α_{eff} (red path in the (ϕ_M, ϕ_ℓ)-plane on the left corresponds to moving along a horizontal line in the ($\alpha_{\text{eff}}, \eta$)-plane).

3.1 Analysis of homogeneous equilibrium states.

We first study the properties of homogeneous equilibrium states that arise in our model. We are specifically interested in how the charge distribution of the polymers, π_z , depends on the mixture composition, ϕ_M and ϕ_ℓ . This is obtained by solving the non-linear system of algebraic equations given by Eqs. (1), (3) and (14)-(16). Generally, this can not be done analytically and requires numerical approaches. However, we make the following observations.

1.) In the case $\eta = 0$ (i.e., independent ion adsorption), the charge distributions π_z is binomial, which can be approximated by a Gaussian distribution in z when taking the maximum charge, $Z \gg 1$;

2.) For z taken as a continuous variable, we can approximate the effective charge regulation free energy $u_{\rm eff}$ as

$$\tilde{u}_{\text{eff}}(z) = z\alpha_{\text{eff}} + \frac{z^2\eta}{2Z} + z\ln\frac{z}{Z} + (Z-z)\ln\left(1-\frac{z}{Z}\right)$$
(20)

in the limit $Z \gg 1$ and $z \in (0, Z)$ (for the details, see A.2). In 2, we summarise how the number and location of the local minima of \tilde{u}_{eff} is controlled by the mixture composition – *i.e.*, the value of the parameter α_{eff} . When \tilde{u}_{eff} has a single minimum, then we can estimate π_z within a saddle-point approximation that we detail in Section V B. We find that for $\eta > -4$, we can approximate the charge distribution by a Gaussian distribution whose mean is determined by the minimum of \tilde{u}_{eff} .

3) The saddle-point approximation is not always valid for $\eta < -4$. The breakdown of the saddlepoint approximation is due to the appearance of multiple extrema for the function \tilde{u}_{eff} (see green area in 2) that is reflected in the charge distribution π_z having multiple peaks. In this case of failure of the saddle-point approximation, we need to resort to numerical methods of computation.

This general feature of unimodality vs. multimodality of the charge distribution is summarised in Figure 2 which displays the $(\eta, \alpha_{\text{eff}})$ diagram. As shown, we can identify two characteristic regimes depending on the value of η : when $\eta > -4$, α_{eff} (*i.e.*, the mixture composition), controls the location of the minimizer of \tilde{u}_{eff} which is always unique; similarly of u_z^{eff} . When $\eta < -4$, α_{eff} (*i.e.*, the mixture composition), controls the location of the number of minimizers of \tilde{u}_{eff} , and likewise of u_z^{eff} . We note that transitions between unimodality to multimodality in charge regulating systems had earlier been seen in [3].

We now discuss the three different cases of interest separately in more detail.

3.1.1 The case $\eta = 0$: independent ion adsorption.

By setting $\eta = 0$, Eqs. (23) are exact and this can be shown without the need of any approximation. Indeed, we have that \mathcal{A} can be evaluated explicitly: $\mathcal{A} = (1 + e^{-\alpha_{\text{eff}}})^{-Z}$. We obtain

$$\pi_z = \binom{Z}{z} p^z \left(1 - p\right)^{Z-z},\tag{21}$$

where

$$p = \frac{e^{-\alpha_{\rm eff}}}{1 + e^{-\alpha_{\rm eff}}}.$$
 (22)

Thus the distribution of polymer states, normalised by the total polymer concentration ϕ_M , has the form of a binomial distribution B(Z, p). We can explain the appearance binomial distribution of the charge state of polymers intuitively. When $\eta = 0$ there is no correlation of different binding sites; thus the state of each of the Z sites can be treated as an independent Bernoulli random variable with probability of success (*i.e.*, binding) equal to p (see Eq. (22)).

3.1.2 $\eta > -4$: the general unimodal case.

When the value of α_{eff} is such that we lie outside the green region in 2, the charge distribution π_z is unimodal with most polymers having a charge state similar to $z \approx Q$, defined as the unique minimizer of (20). As shown in A.2, π_z can be approximated by a Gaussian whose mean charge Q and standard deviation S, can be written as

$$Q = Zp, \quad S^2 = \frac{Zp(1-p)}{\eta p(1-p)+1},$$
 (23a)

where $p \in (0, 1)$ is implicitly defined by

$$p = \frac{e^{-\alpha_{\text{eff}} - p\eta}}{1 + e^{-\alpha_{\text{eff}} - p\eta}}.$$
(23b)

In the case $\eta > -4$, S^2 is guaranteed to be positive independently of the value of $p \in (0, 1)$. When comparing the exact form of Q and S in the case $\eta = 0$ (see 21) and the approximated form for $\eta \neq 0$ (see 23), we find clear parallelisms. When considering $\eta \neq 0$, the model captures the extra energy contributions due to the interaction of the charges on the polymers. Unlike from the case $\eta = 0$, this introduces correlation amongst the state of binding sites (occupied or unoccupied) on the same polymer. Nonetheless, we may still interpret p in 23b as the binding probability for an H⁺ ion to a free binding site. We note that the analogy with the binomial distribution is not exact and difference emerges when comparing the second moments – here the variance S^2 – which explicitly depends on η . When considering states with the same mean charge Q, we have that $\eta > 0$ (short-range repulsion) results in a reduction of the variance of the distribution. In contrast, negative values of η yield to wider distributions, *i.e.*, larger values of S. So far, we have considered α_{eff} as a prescribed parameter. However, as illustrated in 23, α_{eff} is determined by the mixture composition – *i.e.*, the values of ϕ_M and ϕ_ℓ . The computation of the corresponding concentration diagrams requires solving highly non-linear equations, for which existence and uniqueness of solution may not be guaranteed. Due to the physical constraints in the system (no-void and electro-neutrality), homogeneous equilibrium states only exists when ϕ_M and ϕ_ℓ satisfy:

$$1 - \phi_M - \phi_\ell > 0, \tag{24a}$$

$$1 + \phi_M \left(\frac{Z}{N} - 1\right) - 2\phi_\ell > 0,$$
 (24b)

We can prove that such homogeneous states are unique (see Appendix A.3 for details). We obtain the solutions numerically via Newton's method and use the approximation to estimate how Q and S vary as a function of the mixture composition. Results for different values of $\eta > -4$ are shown in 3.

When η is negative (as in 3a), the fully-charged state is the most energetically favourable for the polymers – recall α is also taken to be negative. As a result, whenever the concentration of H⁺-ions in the mixture exceeds the concentration of the binding sites (*i.e.*, $\phi_{\ell} > (Z/N)\phi_M$ – above the dotted light-blue curve in 3), the polymers will be in a fully-charged state– as Q attains its maximum value (see panel (a)) while S its minimum (see panel (b)). In contrast, when the concentration of H⁺-ions in the mixture is lower than the concentration of the binding sites (*i.e.*, $\phi_{\ell} < (Z/N)\phi_M$), the charges are on average distributed homogeneously between the polymers, $Q \approx N\phi_{\ell}/(Z\phi_M)$. This can be shown systematically, by considering the limit $\alpha \rightarrow -\infty$ when estimating p (results not shown). As η increases it becomes less energetically favourable for H⁺-ions to bind to the polymers that tend to remain in a less charged state even when $\phi_{\ell} > (Z/N)\phi_M$. As expected, we find that the largest value of S decreases with η . However, when considering the impact of η on S for a specific mixture composition, there is no general trend. For ion-saturated mixture compositions, S increases with η .

3.1.3 Multi-modal charge distributions: charge demixing.

We now investigate the equilibrium charge distribution for values of $\eta < -4$. As discussed at the beginning of this section, in this regime, the saddle-point approximation breaks down and bimodal charge distributions are expected.

We compute the full charge distribution, $\{\pi_z\}$, solving the non-linear algebraic system given by Eqs. (1), (3) and (14)-(16) using Newton's method with arc-length continuation (used to find good initial guesses for the Newton's step). We conjecture that $\{\pi_z\}$ is still uniquely defined even when we are in regimes for which the charge distribution has multiple peaks (*i.e.*, when we enter the green area in 2); this is strongly supported by our numerical investigation but an analytical proof of the result is beyond the scope of this work.

The results are shown in 4 in which we compare the homogeneous equilibrium states for $\eta = -7$ (left column), $\eta = -5$ (middle column) and $\eta = -2$ (right column). Interestingly, we find that Q is almost insensitive to changes in η (recall that here $\alpha = -6.5 \ll 0$); both below and above the H⁺-saturation curve the mean charge is not affected by increasing of the short-range attractions between bounded charges (*i.e.*, moving from right to left in 4). In contrast, the behaviour of the standard deviation S changes significantly with η ; particularly for mixture compositions below the saturation curve. Overall, we find that the more negative η , the larger the maximum value of S. When $\eta < -4$ (see first and middle column in 4), large values of the variance S are attained by allowing charges to be distributed unevenly between polymers – *i.e.*, π_z has a bimodal profile (see panels (g) and (h) in 4). For values of η near the critical threshold $\eta = -5$ (see panel (h)), we find broad distributions, with polymers in all charge states present in the solution. In this case, the peaks in the distributions occur away from Q (see vertical red line) suggesting that most polymers have a charge state that deviates from the



Figure 3: Composition dependence of mean charge and standard deviation. (a)-(d) Series of surface plots illustrating how the mean charge, Q, depends on the local composition of the mixture (ϕ_M, ϕ_ℓ) , for different values of the parameter η – from left to right: $\eta = -2$; $\eta = 0$; $\eta = 2$ and $\eta = 5$ (short-range repulsion between bounded charges). (e)-(g) Same as panels (a)-(d) but illustrating the computed standard deviation, S. The dotted light blue lines indicate the salt concentration at which the concentration of H⁺ ions in solution equilibrates the concentration of binding sites, *i.e.* $\phi_\ell = Z \phi_M/N$. Other parameters are set to default values given at the start of 3.

mean. As we take $\eta \ll -4$ (see panel (g)), π_z becomes more skewed towards the extreme states, z = 0 and z = 1, and the large values of S are due to the differential partitioning of the charges rather than π_z having a broader support. This is because the intermediate charge states, $z \approx Z/2$, become energetically unfavourable and most polymers exist either in a poorly-charged ($z \approx 0$) or in a highly-charged state ($z \approx 1$). In this regime, changes in the mixture composition only impact the relative fraction of the polymers in poorly-charged and in highly-charged states thus allowing Q to attain all values in the interval [0, Z]. From this point of view, the model could be approximated by a two-population model: either neutral or fully charged polymers that coexist under proper conditions. This is similar to the approach adopted in [1].

3.2 Demixing in solutions of charged polymers

In the previous section we have discussed how charge regulation affects the homogeneous equilibrium states of the mixture. In particular, we find that the mixture composition modulates the equilibrium charge distribution. Due to the physical constraints on the volume fractions – *i.e.*, no-void and electroneutrality – at equilibrium the mixture composition is well-defined by the volume fraction of two species. Here we have chosen: the total volume fractions of polymers, ϕ_M and counterions, ϕ_ℓ .

We now investigate how charge regulation impacts the solubility of charged polymers. The calculation of the phase diagrams follows standard procedures – details are given in Appendix A.4. We denote by $\{\phi_{\omega}^{I}\}$ and $\{\phi_{\omega}^{II}\}$ the volume fraction of species in the dilute (*i.e.*, polymer depleted) and condensed (*i.e.*, polymer rich) phases, respectively. Importantly, in constructing the phase diagrams we allow the



Figure 4: Composition dependence of the mean charge and standard deviation for $\eta < 0$. Series of surface plots illustrating how (a)-(c) Q and (d)-(f), depends on the local composition of the mixture (ϕ_M, ϕ_ℓ) , for different values of the parameter η : (left column) $\eta = -7$; (middle column) $\eta = -5$; and (right column) $\eta = -2$ (same as 3a). The dotted light blue lines indicate the salt concentration at which the concentration of H⁺ ions in solution equilibrates the concentration of binding sites, *i.e.* $\phi_\ell = Z\phi_M/N$. (g)-(i) Plots of the charge distribution, π_z (see (14)) for specific values of (ϕ_M, ϕ_ℓ) (see white dots in panels (a)-(f)); the red vertical lines indicate the mean of the distribution, Q. Other parameters are set to default values given at the start of 3.

ions to be distributed asymmetrically between the dilute and condensed phases. As a result, the tielines (*i.e.*, the curve connecting coexisting states) can have non-zero gradients. This leads to the mean electrostatic potential being different in the dilute (ψ^I) and condensed (ψ^{II}) phases. The difference $\Delta \psi = \psi^{II} - \psi^I$ is known as the *Galvani potential* [37]. For any value of the model parameters the phase diagrams are practically computed in Julia using the <code>BifurcationKit</code> package [33] for numerical continuation.

As mentioned in 2, most models of phase separation assume that the charges on the polymers are fixed. In order to highlight the role of charge regulation in phase separation, we first investigate demixing for a solution of polymers with a fixed charge, Z. While in the charge regulation (CR) model the charge distribution, π_z is obtained by minizing the free energy f (see Eqs (4)-(9)), in a fixed charge (FC) model, π_z is prescribed via a delta function $\pi_z = \delta(z - Z)$. Substituting $\phi_z = \phi_M \delta(z - Z)$ into Eqs. (4)-(9)), we obtain the free energy for the FC model, $f_{\rm FC}$, as

$$\frac{f_{\rm Fc}\nu}{k_BT} = \phi_+ \ln [\phi_+] + \phi_\ell \ln [\phi_\ell] + \phi_s \ln[\phi_s] + \frac{\phi_M}{N} \ln \phi_M + \frac{u_Z \phi_M}{N} + \chi \phi_M \phi_s - \frac{1}{4\pi} \left(\ln(1+\kappa) + \frac{\kappa(\kappa-2)}{2} \right)$$
(25)

where $\kappa = \sqrt{2\lambda\phi_{\ell}}$ (as before) and u_Z is defined as in (7). As before, the system must also satisfy the electro-neutral and no-void constraints (see Eqs. (1) and (3)).

3.2.1 Phase diagrams for macromolecules with a fixed charge.

In 5, we present the phase diagram for increasing values of the fixed charge on the macromolecules, Z. In these diagrams, regions of mixing and demixing are separated by the binodal (or coexistence) curves. Along the binodal, we highlight the gradient of the tie-lines: positive gradients (in red) indicate the counterions concentration is higher in the condensed phase (II); in contrast, negative gradients (in blue) imply counterions accumulate in the dilute phase (I). We note that, besides the constraints (24), in the fixed charge model, the electroneutrality condition also requires $\phi_{\ell} > Z/N\phi_M$.



Figure 5: Phase diagram topologies for polymers with fixed charges. In the different panels, the following fixed charge values Z have been chosen: (a) Z = 0, (b) Z = 5, (c) Z = 10, (d) Z = 15 and (e) Z = 20. The colour scale indicates the gradient of the tie-lines while tie-lines connecting coexisting states are indicated in light grey. The area of the (ϕ_M, ϕ_ℓ) space that are unphysical for our model (*i.e.*, electroneutrality is not satisfied) are shadowed in grey. Critical points at which the two coexisting phases become indistinguishable are denoted by the red circles. Other parameters are set to default values given at the start of 3.

Starting from the case of neutral polymers (see 5a), we recover a coexistence curve analogous to the one obtained in previous works on coacervates [30, 37]. Here the region of demixing is enclosed by a single open curve (the bimodal) and a unique critical point (highlighted in red) exists. Furthermore, the tie-lines have a negative gradient, suggesting that more counterions accumulate in the dilute instead of the condensed phase. The gradient steepens near the critical point, while tie-lines are almost horizontal when the counterions are dilute ($\phi_{\ell}^{(I)} \ll 1$). As we increase Z the fixed charge on the polymers (see 5b-5c), the demixing region is affected only for small values of ϕ_{ℓ} ; this is primarily due to intersection of the bimodal curve with the boundary of the feasibility region ($\phi_{\ell} = Z/N\phi_M$). Since the latter curve has a positive gradient, this enforces the tie-lines to change their orientation as they approach the boundary of the feasibility region. If we increase the charge on the polymers even further (see 5d-5e), we find the demixing region shrinks and its topology changes into a closed-loop with the emergence of a second critical point. We find also a complete inversion in the slope of the tie-lines compared to the neutral case. If we were to increase Z even further, the miscibility gap will disappear (results not shown).

We conclude that overall fixed charges reduce the solubility of polymers in solution.

3.2.2 Phase diagrams for charge-regulating polymers.

In 6, we illustrate the characteristic topologies of the phase diagram for charge-regulating polymers for different values of η . In these diagrams, regions of mixing and demixing are separated by the

binodal curves. In Figures 6a-6d, we depict along the bimodal the mean charge on the polymers, Q. In Figures 6e-6h, we illustrate the same phase diagrams but highlight along the binodal the gradient of the tie-lines (see grey curves). Interestingly, we find that the phase diagrams can be significantly different from each other depending on the value of the charge regulation parameter η . In particular, we find that, for strong short-range repulsion between occupied binding sites, *i.e.*, $\alpha + \eta$ large and negative (first and second column in 6), the phase diagram presents two disconnected regions of demixing namely A and B in 6a)- which are enclosed in the demixing region obtained for neutral polymers (see shaded area in 6a). The demixing region A in 6a lies above the H⁺ saturation curve (see 3a and related discussion) and the polymers effectively behave as having a fixed charge of Z = 20. When comparing region A in 6a (or 6b) and the demixing region in 5e, the two overlap exactly. In contrast, the demixing region B lies fully or partially below the saturation curve. The boundary of this region is delimited by coexisting phases that differ both in the local amount of polymers as well as in their charge state - as highlighted by the variation in the mean charge Q. The implication of these results will be investigated in 3.3. As the value of η increases (*i.e.*, it is less favourable for polymers to be in a fully charged state), the two disconnected regions merge and a single demixing region persists (see 6c). Eventually, for η sufficiently positive, the phase diagram converges to the one of neutral polymers (see 6d).



Figure 6: Phase diagram topologies for different values of the charge regulation parameter η . The following values were chosen: $\eta = -7.0$ (first column); $\eta = -2$ (second column); $\eta = 0$ (third column) and $\eta = 2$ (fourth column). In panels (a)-(d) the colour map indicates the mean charge Q along the binodal curve; the grey area indicates the demixing region for the neutral polymer solution (same as in 5a). In panels (e)-(h), the colour map indicates the gradient of the tie-lines (indicated in light grey). Critical points at which the two coexisting phases become indistinguishable are denoted by red circles. Other parameters are set to default values given at the start of 3.

Interestingly, when comparing phase diagrams with two demixing regions, we find that the tie lines have always a positive gradient – *i.e.*, the concentration of counterions is lower in the dilute (I) instead of condensed phase (II). In contrast, for the phase diagrams with a single demixing region, we observe different trends in the tie-lines: (e)-(g) always a positive gradient; (h) a mix of tie-lines with positive and negative gradients in the proximity of the critical point.

Overall, we find that, similarly to fixed charges, the presence of charge-regulating binding sites lowers the demixing tendency of polymers (compared to the neutral case – see shaded area in 6). Nonethe-

less, we find that charge regulation mechanisms, unlike fixed charges, yield more complex topologies of the phase diagrams. As investigated in the next section, this gives rise to non-linear dependencies between the polymer solubility as a function of the solution acidity.

3.2.3 The impact of counterions on polymer solubility.

Recent studies have focused on studying how chemical properties of salt ions (such as the counterion radii) affect the solubility of charged polymers with fixed charges [7]. Their theoretical results, for a system of polyelectrolytes in a solvent with salt (i.e. positive and negative mobile ions), show non-monotonic salt concentration dependence where salting-out at low salt concentrations is due to ionic screening. In the high salt concentration regime, the macromolecules remain in the salting-out regime for small ions but change to a salting-in regime for larger ions. They conclude that the solubility at high salt concentrations is determined by the competition between the solvation energy and the (translational) entropy of ions, addressing the intensely discussed problem of salt effects in LLPS of protein solutions, such as re-entrant phase transitions shown experimentally in [12, 21].

Here, we are interested analogously in studying the impact of counterions (or solution acidity) on the solubility of charged polymers. We define the solubility, $\omega = \omega(\phi_{\ell})$, of a charged polymer for a given counterion concentration ϕ_{ℓ} , as the minimum value of the equilibrium volume fraction on the binodal curves (see schematic drawing in 7a). Our definition is analogous to the one used in [7], but corrected for the fact that, in our model, multiple coexistence curves may exist.



Figure 7: **Counterion effect on polymer solubility.** (a) Schematic showing how the solubility, ω , is computed starting from the phase diagrams in 3.2 (details in the main text). (b) Solubility ω as a function of the counterion concentration for polymers with different fixed charges (same parameters as in 4a). (c) Solubility ω as a function of the counterion concentrations for charge regulating polymers (same parameters as in Figures 6).

As shown in 7b, we find that for neutral molecules the solubility increases with counterion concentration (see purple curve). In contrast, when considering polymers with fixed charge, ω , has a non-monotonic profile which agrees with the results obtained in [7] (for relatively large salt ions), despite our simpler approximation of electrostatic fluctuations. At low counterion concentrations, the solubility of the polymers decreases with ϕ_{ℓ} . This trend – which we referred to as conterion-out behaviour – is considered to be universal for all ions at low ionic concentrations and is explained by the fact that the counterions are able to screen the charge on the polymers and hence reduce the Coulomb repulsion between the polymers. In contrast, at higher counterion concentrations, the solubility increases with ϕ_{ℓ} – the conterion-in effect. This can be explained by the dominant contribution of the entropy of mixing associated with the ions over charge-screening effects, which favours the miscibility of the solution, very similar to the properties of the system studied in [7].

As shown in 7c, solubility curves of charge-regulating polymers present more complex trends. When $\eta \leq 0$, we find that the solubility curve can be split into three regimes: acid-in at extremely low counterion concentrations; acid-out for intermediate-to-low counterion concentrations; counterion-in at high counterion concentrations. Note that in the transition between the counterion-in at extremely low ϕ_{ℓ} to counterion-out behaviour for low ϕ_{ℓ} , the solubility curve is not smooth. Jumps in ω and ω' is a signature of the presence and merging of the two disconnected demixing regions (see the curves with $\eta \leq 0$ in 7c). For larger values of η (see red curve in 7c), corresponding to the scenario where binding of the ions to the monomers is unfavourable, we recover a monotonic solubility curve as for neutral macro-molecules: consistent counterion-in behaviour (independently of ϕ_{ℓ}).

The transition in the sign of the first derivative from $\omega' > 0$ to $\omega' < 0$ is a signature of another important feature of the phase diagrams in Figure 6a-6c: counterion-driven re-entrant phase separation. Specifically, when short-range repulsion are not too strong (see Figures 6a-6c), the system exhibits re-entrant behaviour when varying the concentration of counterions, ϕ_{ℓ} . In other words, there are values of ϕ_M that lie in the demixing region at very low and high values of ϕ_{ℓ} but not for intermediate (or very high) concentrations of counterions.

3.3 Regulation of the charge distribution via phase separation.

In the previous section, we have shown how charge regulation affects phase separation in solutions of charged polymers. Conversely, in this section, we are interested in how phase separation itself regulates polymer charge in solution. In order to investigate this aspect, we consider a standard quenching experiment where we drive the system to phase separate by controlling the acidity of the solution (*i.e.*, decreasing ϕ_{ℓ}). Specifically, we start from a homogeneous mixture (O) with composition $\phi_M^O = 0.2$ and $\phi_\ell^O = 0.04$; this is then perturbed by decreasing the acid volume fraction to $\phi_\ell = 0.023$. When considering spatially homogeneous equilibria, at any location in space the charge distribution of the polymer phase is the same. However, this is not guaranteed when considering a demixed solution consisting of a dilute (I) and condensed (II) phase. In this case, we denote by π_z^I and π_z^{II} the charge of polymers in each of the two phases. When considering the solution as a whole, the charge distribution on the polymers can be expressed as the weighted average of π_z^I and π_z^{II} :

$$\pi_{z}^{O'} = \frac{\gamma \pi_{z}^{\mathrm{I}} \phi_{M}^{\mathrm{I}} + (1 - \gamma) \pi_{z}^{\mathrm{IP}} \phi_{M}^{\mathrm{II}}}{\gamma \phi_{M}^{\mathrm{I}} + (1 - \gamma) \phi_{M}^{\mathrm{II}}}$$
(26)

where γ is the fraction of the total volume of the solution occupied by the dilute phase (I) in the quenched state (O'). The value of γ is constrained by the conservation of the total concentration of any of the species in the solution; without loss of generality we here consider the conservation of the polymer molecules to obtain:

$$\gamma = \frac{\phi_M^O - \phi_M^{\rm II}}{\phi_M^{\rm I} - \phi_M^{\rm II}}.$$
(27)

As a reference case, we test the protocol on a solution of non-hydrophobic polymers that do not phase separate – see Figure 8A. In this case, decreasing the acid concentration in the solution (*i.e.*, equivalent to decreasing ϕ_{ℓ}) does not lead to phase separation. Yet, it significantly affects the polymer charge distribution (compare Figures 8b and 8c), leading to discharging of the polymer binding sites. In 8B, we consider the same ideal protocol applied to a solution with hydrophobic polymers that phase separates in solution when decreasing the acid volume fraction (see 8d). As shown in 8e, the initial charge distribution on the polymers is similar to the one observed on non-hydrophobic polymers (compare with 8b). Upon quenching, the solution phase separates – state (O') in 8B. Polymers in the dilute phase remain



Figure 8: **Phase separation as a charge regulation mechanism.** Effect of quenching the solution by decreasing the concentration of counterions. We consider two cases: (A) a solution with non-hydrophobic polymers ($\chi = 0$); (B) a solution of hydrophobic polymers that phase separates upon quenching ($\chi = 0.95$). (a) Phase diagram for the case $\chi = 0$ (no demixing). (b) Charge distribution in the initial mixed state (O). (c) Charge distribution, π_z , after the quenching – *i.e.*, homogeneous mixed state (O'). (d) Phase diagram for the case $\chi = 0.95$ (same as in 6c). Decreasing the concentration of counterions drives demixing of the solution into a dilute (I) and condensed (II) phase which are determined by the tie lines. The final state (O') is a demixed solution where 67% of the volume is occupied by the dilute phase while 33% by the condensed phase. (e) Charge distribution in the initial mixed state (O). (f) Local charge distribution for polymer in the condensed phase (II). (g) Local charge distribution for polymer in the condensed phase (II). (g) Local charge distribution for polymer in the condensed phase (II). (g) Local charge distribution for polymer in the condensed phase (I). (h) Overall charge distribution for the demixed mixture (O'). Parameter values are set to default values and $\eta = -2$ (as in 4b).

highly charged (see 8g) as in the initial state (O), whereas polymers in the condensed phase partially discharge (see 8f) as in the case of non-hydrophobic polymers (see 8c). When considering the overall solution, the different charge distribution in the two phases is reflected in the charge distribution $\pi^{O'}$ having multiple peaks – see 8h. By controlling the mixture properties locally – here solution acidity – phase separation creates two environments: the condensed phase where the charge distribution on polymers is highly sensitive to changes in the solution acidity, and the dilute phase where the charge distribution is robust to the changes in acidity. As a result, phase separation allows spatial confinement of polymers with a specific charge state. Note that, after quenching, in 8A, polymers with intermediate charge appear homogeneously in the solution, while these are only localised in the condensed phase in 8B. The possible functional implication of these findings in the context of biomolecular condensates will be discussed in the next section.

4 Conclusions and Discussion

In this work, we considered a minimal model to investigate the interplay of phase separation and charge regulation. For this, we introduced in 2 a system of chargeable polymers, whose charge state is regulated by protonation/ deprotonation processes, in a water-acid solution.

In 3.1, we established the homogeneous equilibria states of the system focusing on how the mixture composition – *i.e.*, the concentration of the polymers, ϕ_M , and the counterions, ϕ_ℓ – affects the polymer charge distribution. In doing so, we employed analytical findings which highlighted the key role of the parameter η , describing bounded charge interactions, in determining the properties of equilibrium

charge distribution.

Our key findings are: For $\eta = 0$, the charge distributions in homogeneous states of the system simplified considerably and it can be found to follow a binomial distribution. For $\eta \neq 0$ we showed that by approximating the charge interaction as a continuous function, we can approximate the charge distribution by a Gaussian distribution for a continuous variable in the limit of a large number of charges, as we derive within a saddle-point approximation. Our analysis yielded that for $\eta < -4$, this approximation ceases to be generally valid, as multi-modal distributions can arise depending on the mixture composition.

In 3.2, we unfolded how charge regulation processes affect phase diagrams of polymer solutions. To do so, we first characterised phase diagrams assuming a fixed charge on the polymers; we then investigated how the topology changes by introducing charge regulation mechanisms. We found that charge regulation processes can affect the phase diagram topology in a nontrivial manner: upon decreasing η , we observed that the usual demixing region undergoes a change of its topology, in which a closed-loop region branches off from the original demixing region – which persists. This contrasts with the phase diagrams of polymers with fixed charges, where at most one demixing region exists. The complex topology of the phase diagram is reflected in the relation between counterions concentration and polymer solubility (in short solubility curves) in an acid-water solution. We find that charge regulation mechanisms have a prominent signature: depending on the charge-interaction parameter η , due to the re-entrant phase behaviour induced by charge regulation, the solubility curve can exhibit a pronounced jump. This might be a relevant experimental signature for the charge-regulation induced transition in the topology of coexistence curves.

In addition, our results show that charge regulation has an important impact on the partitioning of counter-ions and thus the gradients of the corresponding tie-lines, which is further complicated by the existence of multi-modal equilibrium states. These findings add to the discussion on salt-partitioning in the complex coacervation of polyelectrolyte [31]. Different theoretical frameworks – *e.g.*, random phase approximation (RPA) which includes connectivity of the polyelectrolyte, and Liquid-State theories– have been proposed to explain salt partitioning and tie-lines gradients. Identifying the physical reasons for salt partitioning amongst the increasing number of candidate theories remains an open problem and an active area of research [31]. Our results suggest that allowing for charge regulation can also affect tie-lines gradient thus adding yet another layer to this discussion.

In the last section, 3.3, we investigated the effect phase separation has on the charge distribution. By discussing an experimental scenario in which the concentration of counterions in the polymer solution is changed, we demonstrated that phase separation can create local environments with very different charge distributions in the dilute and condensed phases, which in addition are either very similar or quite different from the initial state. Our findings highlight how charge regulation mechanisms can have a significant role in the response of polymer solutions to changes in the physical environment, by introducing a complex coupling between processes occurring at the micro-scale (protonation/deprotonation) and meso-scale (phase separation). Interestingly, similar non-linear effects – like e.g. re-entrant phase behaviour– have been recently discussed by Jacobs et al. in a seemingly unrelated system, in which a different molecular process - polymer self-assembly - is discussed in conjunction with phase separation [15]. This suggests re-entrant behaviour might be a general feature of systems where phase separation is coupled to a molecular mechanism (such as charge regulation or self-assembly).

On the one hand, charge regulation controls the sensitivity of polymer solutions to environmental changes by allowing for so-called re-entrant demixing behaviour. We expect this non-linear dependence of phase separation on environmental cues to be fundamental in a range of applications to

soft matter science, such as in the design of responsive materials, as well as in LLPS of proteins. Salt-induced re-entrant phase separation has been observed for proteins that undergo LLPS in the high-salt regime [12], including the intensively investigated protein FUS. These observations, together with our and previous theoretical works [1] show the impact of the environment as a driving force of LLPS and adds a further important mechanism to the widely discussed sequence-dependence LLPS of intrinsically disordered proteins.

Conversely, we also find that by affecting the local environment the polymers are in, phase separation itself can regulate the polymer charge state by allowing to spatially confine polymers in a specific charged state – hence increasing their local volume fraction. This can have important consequences when considering polymers interacting with additional chemical agents, whereby their interactions may be mediated by the polymer charge state. This is the case in the cell cytoplasm. From this point of view, phase separation in cells might function as a regulator of cellular responses to the environment by controlling both the location, as well as the charge state of proteins.

Despite its simplicity, our model yields a rich and interesting range of behaviours that hint at the importance of charge regulation mechanisms in the formation and properties of condensates. There is therefore scope to extend our theory to investigate whether our findings have relevance to LLPS in cells. This requires extending our model to account for the complexity of biological macromolecules – such as RNA and proteins. For example, in this work, we have assumed the interaction parameter χ to be independent of the polymer charge state. However, when considering short-range interactions e.g. between polymer chains, these are known to be charge-dependent. Therefore, a further natural extension of this work would be to analyse the scenario in which χ is considered a function of the charge state z. This would result in the mixture composition influencing not only the association–dissociation energy parameter, α , but also higher-order interactions between binding sites.

Overall, our results reveal that, even in the simplest system consisting of one polymer species whose charge states undergo a protonation/deprotonation process, the interplay between phase separation and charge regulation mechanisms governs the response of polymer mixtures to environmental changes.

Acknowledgements

The authors thank Dr Matthew Hennessy and Prof. Sarah Waters for the helpful discussions in the initial phase of this project.

References

- [1] Omar Adame-Arana, Christoph A. Weber, Vasily Zaburdaev, Jacques Prost, and Frank Jülicher. Liquid Phase Separation Controlled by pH. *Biophysical Journal*, 119(8):1590–1605, oct 2020.
- [2] Yael Avni, David Andelman, and Rudolf Podgornik. Charge regulation with fixed and mobile charged macromolecules. *Current Opinion in Electrochemistry*, 13:70–77, 2019.
- [3] Yael Avni, Rudolf Podgornik, and David Andelman. Critical behavior of charge-regulated macroions. *The Journal of Chemical Physics*, 153(2):024901, 2020.

- [4] Clifford P Brangwynne, Peter Tompa, and Rohit V. Pappu. Polymer physics of intracellular phase transitions. *Nature Physics*, 11:899–904, 2015.
- [5] Jeong-Mo Choi, Alex S. Holehouse, and Rohit V. Pappu. Physical principles underlying the complex biology of intracellular phase transitions. *Annual Review of Biophysics*, 49(1):107–133, 2020.
- [6] Fernando Luís Barroso da Silva, Philippe Derreumaux, and Samuela Pasquali. Protein-RNA complexation driven by the charge regulation mechanism. *Biochemical and biophysical research communications*, 498(2):264–273, 2018.
- [7] Chao Duan and Rui Wang. Understanding the salt effects on the liquid-liquid phase separation of proteins, 2023.
- [8] S. W. Englander, L. Mayne, Y. Bai, and T. R. Sosnick. Hydrogen exchange: The modern legacy of Linderstrøm-Lang. *Protein Science*, 6(5):1101–1109, 1997.
- [9] Martin J. Fossat, Ammon E. Posey, and Rohit V. Pappu. Quantifying charge state heterogeneity for proteins with multiple ionizable residues. *Biophysical Journal*, 120:5438–5453, 2021.
- [10] Sean Friedowitz, Ali Salehi, Ronald G. Larson, and Jian Qin. Role of electrostatic correlations in polyelectrolyte charge association. *The Journal of Chemical Physics*, 149(16), 09 2018. 163335.
- [11] Jing Hua, Mithun K. Mitra, and M. Muthukumar. Theory of volume transition in polyelectrolyte gels with charge regularization. *The Journal of Chemical Physics*, 136(13):134901, 2012.
- [12] Georg Krainer, Timothy J Welsh, Jerelle A Joseph, Jorge R Espinosa, Sina Wittmann, Ella de Csilléry, Akshay Sridhar, Zenon Toprakcioglu, Giedre Gudiškytė, Magdalena A Czekalska, et al. Reentrant liquid condensate phase of proteins is stabilized by hydrophobic and non-ionic interactions. *Nature communications*, 12(1):1085, 2021.
- [13] Sunita Kumari, Shikha Dwivedi, and Rudolf Podgornik. On the nature of screening in Voorn–Overbeek type theories. *The Journal of Chemical Physics*, 156(24), 06 2022. 244901.
- [14] Yan Levin. Electrostatic correlations: from plasma to biology. *Reports on Progress in Physics*, 65(11):1577, sep 2002.
- [15] Tianhao Li, Benjamin Rogers, and William M. Jacobs. Interplay between self-assembly and phase separation in a polymer-complex model. *arXiv:2306.13198*, 2023.
- [16] Yi-Hsuan Lin, Julie D. Forman-Kay, and Hue Sun Chan. Sequence-specific polyampholyte phase separation in membraneless organelles. *Phys. Rev. Lett.*, 117:178101, Oct 2016.
- [17] Esteban Meca, Anatol W. Fritsch, Juan M. Iglesias-Artola, Simone Reber, and Barbara Wagner. Predicting disordered regions driving phase separation of proteins under variable salt concentration. *Frontiers in Physics*, 11, 2023.
- [18] M. Muthukumar, Jing Hua, and Arindam Kundagrami. Charge regularization in phase separating polyelectrolyte solutions. *The Journal of Chemical Physics*, 132(8):084901, 2010.
- [19] RJ Nap, B Qiao, Palmer LC, SI Stupp, M Olvera de la Cruz, and I Szleifer. Acid-base equilibrium and dielectric environment regulate charge in supramolecular nanofibers. *Front Chem.*, (10), 2022.

- [20] Timothy J Nott, Evangelia Petsalaki, Patrick Farber, Dylan Jervis, Eden Fussner, Anne Plochowietz, Timothy D Craggs, David P Bazett-Jones, Tony Pawson, Julie D Forman-Kay, et al. Phase transition of a disordered nuage protein generates environmentally responsive membraneless organelles. *Molecular cell*, 57(5):936–947, 2015.
- [21] Seung-Hwan Oh, Jinhoon Lee, Minhwan Lee, Seulwoo Kim, Won Bo Lee, Dong Woog Lee, and Soo-Hyung Choi. Simple coacervation of guanidinium-containing polymers induced by monovalent salt. *Macromolecules*, 56(11):3989–3999, 2023.
- [22] J. T. G. Overbeek and M. J. Voorn. Phase separation in polyelectrolyte solutions. theory of complex coacervation. *Journal of Cellular and Comparative Physiology*, 49(S1):7–26, 1957.
- [23] C Nick Pace, Gerald R Grimsley, and J Martin Scholtz. Protein ionizable groups: pK values and their contribution to protein stability and solubility. *Journal of Biological Chemistry*, 284(20):13285–13289, 2009.
- [24] Jian Qin and Juan J. de Pablo. Criticality and connectivity in macromolecular charge complexation. *Macromolecules*, 49:8789–8800, 2016.
- [25] Joshua A. Riback, Lian Zhu, Mylene C. Ferrolino, Michele Tolbert, Diana M. Mitrea, David W. Sanders, Ming-Tzo Wei, Richard W. Kriwacki, and Clifford P. Brangwynne. Composition-dependent thermodynamics of intracellular phase separation. *Nature*, 581:1476–4687, 2020.
- [26] Artem M Rumyantsev, Nicholas E Jackson, and Juan J De Pablo. Polyelectrolyte complex coacervates: Recent developments and new frontiers. *Annual Review of Condensed Matter Physics*, 12:155–176, 2021.
- [27] Ali Salehi and Ronald G. Larson. A molecular thermodynamic model of complexation in mixtures of oppositely charged polyelectrolytes with explicit account of charge association/dissociation. *Macromolecules*, 49(24):9706–9719, 2016.
- [28] Daniel Mark Shapiro, Max Ney, Seyed Ali Eghtesadi, and Ashutosh Chilkoti. Protein phase separation arising from intrinsic disorder: First-principles to bespoke applications. *The Journal of Physical Chemistry B*, 125(25):6740–6759, 2021.
- [29] Kevin Shen and Zhen-Gang Wang. Electrostatic correlations and the polyelectrolyte self energy. *The Journal of Chemical Physics*, 146(8), 02 2017. 084901.
- [30] Charles E. Sing. Development of the modern theory of polymeric complex coacervation. Advances in Colloid and Interface Science, 239:2–16, 2017. Complex Coacervation: Principles and Applications.
- [31] Charles E. Sing and Sarah L. Perry. Recent progress in the science of complex coacervation. *Soft Matter*, 16:2885–2914, 2020.
- [32] Charles Tanford and John G Kirkwood. Theory of protein titration curves. i. general equations for impenetrable spheres. *Journal of the American Chemical Society*, 79(20):5333–5339, 1957.
- [33] Romain Veltz. BifurcationKit.jl, July 2020.
- [34] Jose Villegas, Meta Heidenreich, and Emmanuel D. Levy. Molecular and environmental determinants of biomolecular condensate formation. *Nature Chemical Biology*, 18:1319–1329, 2022.

20

- [35] Evgenee Yekymov, David Attia, Yael Levi-Kalisman, Ronit Bitton, and Rachel Yerushalmi-Rozen. Charge regulation of poly(acrylic acid) in solutions of non-charged polymer and colloids. *Polymers*, 15(5), 2023.
- [36] Pengfei Zhang, Nayef M. Alsaifi, Jianzhong Wu, and Zhen-Gang Wang. Polyelectrolyte complex coacervation: Effects of concentration asymmetry. J. Chem. Phys., 149(16):163303, October 2018.
- [37] Pengfei Zhang and Zhen-Gang Wang. Interfacial structure and tension of polyelectrolyte complex coacervates. *Macromolecules*, 54(23):10994–11007, 2021.
- [38] Xuemei Zhang, Michael Vigers, James McCarty, Jennifer N Rauch, Glenn H Fredrickson, Maxwell Z Wilson, Joan-Emma Shea, Songi Han, and Kenneth S Kosik. The prolinerich domain promotes tau liquid–liquid phase separation in cells. *Journal of Cell Biology*, 219(11):e202006054, 2020.
- [39] Bin Zheng, Yael Avni, David Andelman, and Rudolf Podgornik. Phase Separation of Polyelectrolytes: The Effect of Charge Regulation. *The Journal of Physical Chemistry B*, page acs.jpcb.1c01986, jul 2021.

A Appendix

A.1 Derivation of the chemical potential condition

We consider an incompressible mixture in the (T, V, N)-ensemble with temperature T, volume V and particle numbers N_{ω} - where $\omega \in \Omega$. At equilibrium, such a system minimises the Helmholtz free energy, $F = F(T, V, \{N_{\omega}\}_{\omega \in \Omega})$. From Euler's relation, it follows that

$$F(T, V, \{N_{\omega}\}_{\omega \in \Omega}) = \sum_{\omega \in \Omega} \mu_{\omega} N_{\omega} - pV,$$
(28)

where p is the pressure and μ_{ω} are the chemical potentials of the different components of the mixture. Incompressibility of the mixture implies that the molecular volume ν_{ω} of each component of the mixture is constant; as a result, the volume of the mixture can not be taken as an independent variable but rather as a function of the particles numbers: $V = \sum_{\omega \in \Omega} N_{\omega} \nu_{\omega}$. Differentiation of F with respect to particle number leads to the chemical potential condition

$$\mu_{\omega} = \frac{\partial F}{\partial N_{\omega}} + p\nu_{\omega} \,. \tag{29}$$

Transforming now to the Helmholtz free energy density $f(T, \{\phi_{\omega}\}_{\omega \in \Omega}) = F/V$ with the volume fractions $\phi_{\omega} = N_{\omega}\nu_{\omega}/V$ we obtain, performing the necessary differentiations,

$$\mu_{\omega} = \nu_{\omega} f + \nu_{\omega} \frac{\partial f}{\partial \phi_{\omega}} + V \nu_{\omega} \sum_{\sigma} \frac{\partial f}{\partial \phi_{\sigma}} \frac{(-\nu_{\sigma} N_{\sigma})}{V^2} + \nu_{\omega} p$$

$$= \nu_{\omega} \left[p + \left(f - \sum_{\sigma} \frac{\partial f}{\partial \phi_{\sigma}} \phi_{\sigma} \right) \right] + \nu_{\omega} \frac{\partial f}{\partial \phi_{\omega}}.$$
(30)

Applying this general relation to our mixture we find that the chemical potential of the free ions (μ_+ , μ_ℓ), solvent (μ_s) and *z*-charged polymers (μ_z) are given by

$$\mu_{+} = (p - \Sigma)\nu + k_{B}T \left[\ln(\phi_{+}) + 1 - \frac{\lambda}{8\pi} \frac{\kappa}{1 + \kappa} \right], \qquad (31)$$

$$\mu_{\ell} = (p - \Sigma)\nu + k_B T \left[\ln(\phi_{\ell}) + 1 - \frac{\lambda}{8\pi} \frac{\kappa}{1 + \kappa} \right],$$
(32)

$$\mu_s = (p - \Sigma)\nu + k_B T [\ln(\phi_s) + 1 + \chi \phi_M],$$
(33)

$$\mu_{z} = (p - \Sigma)N\nu$$

$$+ k_{B}T \left[u_{z} + \ln(\phi_{z}) + 1 + \chi N\phi_{s} - \frac{z\lambda}{8\pi} \frac{\kappa}{1 + \kappa} \right].$$
(34)

The expression for Σ arises from those terms in the round brackets in (30) that do not cancel out which is only the case for contributions from f_2 and f_3 . Making use of the no-void condition for f_2 and the electroneutrality condition for f_3 one finds

$$\frac{\nu\Sigma}{k_BT} = \left(1 - \phi_M + \frac{\phi_M}{N}\right) + \chi \phi_M \phi_s + \frac{1}{4\pi} \left(\ln(1+\kappa) - \frac{\kappa}{2} \frac{2+\kappa}{1+\kappa}\right).$$
(35)

A.2 Saddle-point approximation

When considering $\eta = 0$, the charge distribution, $\{\pi_z\}_{z=0}^Z$, is binomial. It is well known that a general binomial distribution, B(Z, p), is well-approximated by a Gaussian distribution with the same mean and standard deviation, in the limit $Z \gg 1$ – provided p is bounded away from its extreme values 0 and 1. Here we show that a saddle-point approximation to the charge distribution is possible provided that $\eta > -4$, guaranteeing that the charge distribution has a unique maximum.

Substituting the definition of u_z (see (7)) into (14), we obtain that π_z reads

$$\pi_z = \frac{\exp\left(-\alpha_{\text{eff}}z - \frac{\eta z^2}{2Z} + \ln\left[\binom{Z}{z}\right]\right)}{\sum\limits_{k=0}^{Z} \exp\left(-\alpha_{\text{eff}}k - \frac{\eta k^2}{2Z} + \ln\left[\binom{Z}{k}\right]\right)}, \quad z = 0, \dots, Z.$$
(36)

where the α_{eff} is as defined in (18b). In what follows, we want to approximate the distribution (36) by a Gaussian distribution centred at its mean value $\mathcal{Q} = \sum_{z=0}^{Z} z\pi_z$ under the assumption that $Z \gg 1$. For our approximation to be valid, the mean charge needs to be sufficiently far from its extreme values, *i.e.*, $\mathcal{Q} \gg 0$ and $Z - \mathcal{Q} \gg 0$. Since $Z \gg 1$, we rewrite the discrete charge distribution (36), as a continuous probability distribution for the continuous variable $z \in [0, Z]$. First, we approximate the binomial coefficient by using Stirling's series:

$$\ln(n!) \approx n \ln n - n + \frac{1}{2} \ln(2\pi n) + O\left(\frac{1}{n}\right).$$
(37)

Using (37), we find

$$\frac{1}{Z}\ln\left[\binom{Z}{z}\right] = -\frac{z}{Z}\ln\frac{z}{Z} - \left(1 - \frac{z}{Z}\right)\ln\left(1 - \frac{z}{Z}\right)
- \frac{1}{2Z}\ln\left(2\pi z\left(1 - \frac{z}{Z}\right)\right)
+ O\left(\frac{1}{Zz}\right) + O\left(\frac{1}{Z(Z-z)}\right),$$
(38)

Following the continuous approximation, we can write (36) but considering $z \in (0, Z)$ as a continuous distribution:

$$\pi_z = \frac{\exp\left(-Z\tilde{u}_{\text{eff}}\left(\frac{z}{Z}\right)\right)}{Z\int_0^1 \exp\left(-Z\tilde{u}_{\text{eff}}(\omega)\right)d\omega}, \quad z \in (0, Z),$$
(39a)

where

$$\begin{split} \tilde{u}_{\text{eff}}(\omega) &= \omega \alpha_{\text{eff}} + \frac{\omega^2 \eta}{2} + \omega \ln \omega \\ &+ (1 - \omega) \ln(1 - \omega) + h.o.t. \end{split} \tag{39b}$$

By computing the second derivative of \tilde{u}_{eff} , it is apparent that for $\eta > -4$ the function \tilde{u}_{eff} is convex for $\omega \in (0, 1)$. This guarantees that there exists a unique minimum, $p \in (0, 1)$. As discussed in 3.1, we can interpret p as an effective binding probability of ions to the polymer that we have defined in the main text. An implicit definition for p can be obtained by solving $\tilde{u}'_{\text{eff}}(p) = 0$:

$$p = \frac{e^{-\alpha_{\text{eff}} - p\eta}}{1 + e^{-\alpha_{\text{eff}} - p\eta}}.$$
(40)

When $Z \gg 1$, the mass of the normalisation integral (see first factor in 39a) will be localised around the stationary point, p, and standard techniques, such as Laplace's method can be applied:

$$\int_{0}^{1} e^{-Z\tilde{u}_{\text{eff}}(\omega)} d\omega \approx \sqrt{\frac{2\pi}{Z\tilde{u}''_{\text{eff}}(p)}} e^{-Z\tilde{u}_{\text{eff}}(p)},\tag{41}$$

where

$$\tilde{u}_{\text{eff}}(p) = -\frac{\eta p^2}{2} - \ln\left(1 + \frac{\phi_+}{\phi_s}e^{-\alpha - \chi\phi_M - p\eta}\right),\tag{42a}$$

$$\tilde{u}_{\rm eff}''(p) = \frac{\eta p(1-p) + 1}{p(1-p)}.$$
(42b)

Substituting the above into 39a and expanding around the stationary point (Zp), we obtain a Gaussian distribution:

$$\pi_z \approx \frac{1}{\sqrt{2\pi Z \tilde{u}_{\text{eff}}''(p)}} \exp\left(-\frac{(z-Zp)^2}{2Z \tilde{u}_{\text{eff}}''(p)}\right).$$
(43)

In 9, we compare the approximated distribution (43) with the real distribution (36) for different values of α_{eff} . We find good agreement between the two. Nonetheless, discrepancies emerge when considering $|\alpha_{\text{eff}}| \gg 1$ when the maximum of the distribution shifts towards the boundary of the domain: for α_{eff} large and negative, the maximum $\approx Z$ while for α_{eff} large and positive ≈ 0 . This discrepancy is to be expected since for the approximation to hold we must assume p is bounded away the extreme values 0 and 1.



Figure 9: **Saddle-point approximation.** Plots comparing the exact discrete distribution (36) (histogram) and its approximation obtained via the saddle-point approach (43) (red curve). Different panels corresponds to different choices of the parameter α_{eff} .

A.3 Unimodal distribution: domain of physicality.

In this section, we outline results on the existence and uniqueness of the effective binding probability p (see (23b)) assuming $\eta > -4$ for any values of $\phi_M \in (0, 1)$ and $\phi_\ell \in (0, 1)$ which are physically allowed.

By substituting (23) into (1)-(3), we find that p is implicitly defined by the non-linear algebraic equation $\Pi_{\eta}(p) = 0$, where

$$\Pi_{\eta}(x) = e^{x\eta}x \left(1 - \phi_M - \phi_\ell\right)$$

$$+ \left(\frac{Zx}{N}\phi_M - \phi_\ell\right) \left[xe^{\eta x} + e^{-\alpha - \chi\phi_M}(1-x)\right].$$
(44)

The form of Π_{η} is obtained starting from (40) and (18b) by first eliminating ϕ_{+} via (3) in the form $\phi_{+} = \phi_{\ell} - Zp/N\phi_{M}$, and by finally using (1) in the form $\phi_{s} = 1 + (Zp/N - 1)\phi_{M} - 2\phi_{\ell}$ to eliminate the remaining dependence on ϕ_{s} . Note that when setting $\eta = 0$, Π_{0} reduces to a quadratic equation for p_{0} that can be solved explicitly:

$$p_0 = \frac{-b(\phi_M, \phi_\ell) + \sqrt{b^2(\phi_M, \phi_\ell) + 4c(\phi_M, \phi_\ell)}}{2},$$
(45a)

where

$$b(\phi_M, \phi_\ell) = \frac{N}{Z} \frac{1 - \phi_M - 2\phi_\ell + e^{-\alpha - \chi\phi_M} (Z/N\phi_M + \phi_\ell)}{(1 - e^{-\alpha - \chi\phi_M})\phi_M},$$
(45b)

$$c(\phi_M, \phi_\ell) = \frac{N}{Z} \frac{\phi_\ell e^{-\alpha - \chi \phi_M}}{(1 - e^{-\alpha - \chi \phi_M})\phi_M}.$$
(45c)

Nonetheless, we consider the more general case $\eta > -4$, and prove that there exists at most one root p for the function Π_{η} in the interval (0, 1]; conditions for existence are then discussed. We here exclude 0 since p = 0 refers to the critical case where no counter-ions are present in the solution: $\Pi_{\eta}(0) = -e^{-\alpha - \chi \phi_M} \phi_{\ell} = 0$ only if $\phi_{\ell} = 0$. First, we note that, for $x \in (0, 1]$, the first term on the right hand side in (44) is always non-negative (since from the no-void condition $\phi_s + \phi_+ = 1 - \phi_{\ell} - \phi_M \ge 0$). The sign of the second term instead depends on the value of $(Zx/N)\phi_M - \phi_{\ell}$. Given that p is a root of Π_{η} , if that exists, we must have that $Zp/N\phi_M - \phi_{\ell} < 0$ (which guarantees that $\phi_+ > 0$).

We now consider the value of the first derivative of Π_{η} and evaluate it at one of its possible roots:

$$\Pi'_{\eta}(p) = \frac{Z}{N} \phi_M \left(p e^{p\eta} + e^{-\alpha - \chi \phi_M} (1-p) \right)$$

$$+ \left(\phi_\ell - \frac{Zp}{N} \phi_M \right) e^{-\alpha - \chi \phi_M} \frac{1 + \eta p (1-p)}{p},$$
(46)

where we have used the fact that $\Pi_{\eta}(p) = 0$. It is apparent that the first term in (46) is positive and so is the second term, since, as discussed above, we must have that $\phi_{\ell} - Z/Np\phi_M > 0$. This implies that for any root of $\Pi_{\eta}, p \in (0, 1]$, the derivative $\Pi'_n(p) > 0$. **Uniqueness.** Since the function Π_{η} is analytic and $\Pi'_{\eta}(p) > 0$, we conclude that if p exists this must be unique. Otherwise, there would exists a root $\tilde{p} \in (0, 1)$ such that $\Pi'_{\eta}(\tilde{p}) \leq 0$.

Existence. Generally, the existence of p is not guaranteed. Since $\Pi_{\eta}(0) < 0$, the only conditions for the existence of p is that $\Pi_{\eta}(1) \ge 0$:

$$1 - \phi_M - 2\phi_\ell + \frac{Z}{N}\phi_M > 0.$$
(47)

Domain of physicality. Summarising the results above, we find two inequality constraints that homogeneous equilibria exist (*i.e.*, p is well-defined) provided that:

$$1 - \phi_M - \phi_\ell > 0, \tag{48a}$$

$$1 + \phi_M \left(\frac{Z}{N} - 1\right) - 2\phi_\ell > 0.$$
 (48b)

However, for the equilibria to be physical meaning, we must have that the corresponding volume fractions ϕ_+ and ϕ_s are positive and less than one. Conditions (48) are sufficient to guarantee this is the case.

A.4 Two-phase coexistence conditions

In this section, we derive the coexistence conditions used to compute the phase diagrams presented in 3.2. We start by considering an initially homogeneous mixture of the Z+4 species that has been quenched into the unstable regime, just before separates into two phases. Each of the emerging phases are homogeneous with a unique composition, characterised by the composition vectors ϕ^I_ω and ϕ^{II}_ω . In the *demixed* state, the conditions for the coexistence of two phases are

$$\mu(\{\phi_{\omega}^{I}\}_{\omega\in\Omega}) = \mu(\{\phi_{\omega}^{II}\}_{\omega\in\Omega}).$$
(49)

These are Z + 4 conditions for 2(Z + 4) variables, leaving Z + 4 degrees of freedom. For the charge regulation (CR) model, we assume each phase is in chemical equilibrium, which imposes the chemical potentials in each of the two phases to satisfy Eq. (10), or Z restrictions each. When considering the fixed charge (FC) model, the system is constrained by imposing the charge distribution $\pi_z = \delta(z - Z)$ in both phases; also in the latter case, this leads to 2Z restrictions. However, due to the equality of chemical potentials between phases, we only need to impose these Z conditions on one phase (for the other they are then implied). So we have 4 degrees of freedom left. We also have to satisfy electroneutrality and no-void in each phase, which removes all four remaining degrees of freedom. As a result, we lack one degree of freedom required to match those of the initial homogeneous mixture prior to demixing.

This problem is frequently addressed by adding an additional contribution to the chemical potential μ_{ω} in (31) for each of the charged species, giving rise to the electrochemical potential,

$$\check{\mu}_{\omega} = \mu_{\omega} + z_{\omega} e \psi, \tag{50}$$

where ψ is the Galvani potential. These electrochemical potentials are then equated instead of the chemical potentials. In a homogeneous system, the Galvani potential ψ is constant and hence can be eliminated by setting it to zero, but in a non-homogeneous e.g. demixed system it is usually not.

We then have two different values for ψ and the difference between the two remains as the previously missing additional degree of freedom.

Here, we proceed differently to motivate the introduction of a Galvani potential and describe the phase separation as a minimisation problem. We again consider a system with two coexisting phases and a total volume V = 1 (without loss of generality), split into two sub-systems I and II of volume γ and $1 - \gamma$, respectively, with $0 < \gamma < 1$. Each subsystem is occupied by a single, in itself homogeneous phase described by the variables $\phi^I = (\phi^I_{\omega})_{\omega \in \Omega}$ and $\phi^{II} = (\phi^{II}_{\omega})_{\omega \in \Omega}$, respectively. The total free energy of the demixed system is then given by

$$F_2 = \gamma f(\boldsymbol{\phi}^I) + (1 - \gamma) f(\boldsymbol{\phi}^{II}).$$
(51)

In a system without chemical reactions, each species is individually subject to mass conservation and we would minimise F under these Z + 4 constraints to find the equilibrium of the system. With chemical reactions, a smaller number of quantities are conserved, and these quantities need to be determined in an additional step prior to the formulation of the minimisation problem. For this purpose, note that the total number of molecules of species ω present is given by

$$N_{\omega} = \left(\gamma \phi_{\omega}^{I} + (1 - \gamma) \phi_{\omega}^{II}\right) / \nu_{\omega}$$
(52)

For

$$K = \sum_{\omega \in \Omega} a_{\omega} N_{\omega} \tag{53}$$

to be conserved, the vector $oldsymbol{a}=(a_\omega)_{\omega\in\Omega}$ has to satisfy

$$\mathbb{S}^T \boldsymbol{a} = 0, \tag{54}$$

where \mathbb{S} is the stoichiometric matrix (with Z+4 rows and Z columns), that is, the rows of its transpose are the stoichiometric coefficients of the chemical reactions. To write out this matrix, we assume that the indices ω are ordered as $z = 0, 1, \ldots, Z$ followed by $s, +, \ell$. Then we get

$$\mathbb{S}^{T} = \begin{bmatrix} -1 & 1 & 0 & 0 & \dots & 1 & -1 & 0 \\ 0 & -1 & 1 & 0 & \dots & 1 & -1 & 0 \\ \vdots & \ddots & \ddots & \ddots & \ddots & \vdots & \vdots & \vdots \\ 0 & 0 & \dots & -1 & 1 & 1 & -1 & 0 \end{bmatrix}.$$
(55)

Four linearly independent solutions a of (54) can be easily read off and give the conserved quantities

$$K_1 = \nu N_\ell = \gamma \phi_\ell^I + (1 - \gamma) \phi_\ell^{II}, \tag{56a}$$

$$K_{2} = \nu \left(N_{s} + N_{+} \right) = \gamma \left(\phi_{s}^{I} + \phi_{+}^{I} \right) + \left(1 - \gamma \right) \left(\phi_{s}^{II} + \phi_{+}^{II} \right),$$
(56b)

$$K_{3} = \nu_{M} \sum_{z=0}^{Z} N_{z} = \gamma \sum_{z=0}^{Z} \phi_{z}^{I} + (1 - \gamma) \sum_{z=0}^{Z} \phi_{z}^{II},$$
(56c)

$$K_{4} = \nu \left(\sum_{z=0}^{Z} z N_{z} + N_{+}\right)$$

$$= \gamma \left(\frac{\nu}{\nu_{M}} \left(\sum_{z=0}^{Z} z \phi_{z}^{I}\right) + \phi_{+}^{I}\right)$$

$$+ (1 - \gamma) \left(\frac{\nu}{\nu_{M}} \left(\sum_{z=0}^{Z} z \phi_{z}^{II}\right) + \phi_{+}^{II}\right)$$
(56d)

In the minimisation problem for F_2 in (51), we enforce that the $K_i \equiv K_i(\phi^I, \phi^{II}, \gamma)$ are equal to a constant parameter K_i^0 , the value of which is set for example by the composition of the mixture prior to separation into two phases. We impose the resulting conditions as constraints, alongside the no-void (1) and electroneutrality (3) conditions enforced separately for each of the two phases. However, it turns out that (56c) is implied by (56a), (56b) and the no-void condition (1), and therefore can be dropped. Similarly, (56d) is implied by (56a) and electroneutrality (3), so this constraint can be dropped, too.

Including the constraints via Lagrange multipliers λ_1 , λ_2 , ρ^I , ρ^{II} and ψ^I , ψ^{II} , we seek the stationary points of

$$L_{2} = F_{2} + \lambda_{1}(K_{1} - K_{1}^{0}) + \lambda_{2}(K_{2} - K_{2}^{0}) + \rho^{I} \left(\sum_{\omega \in \Omega} \phi_{\omega}^{I} - 1\right) + \rho^{II} \left(\sum_{\omega \in \Omega} \phi_{\omega}^{II} - 1\right) + \psi^{I} e \gamma \left(\phi_{+}^{I} - \phi_{\ell}^{I} + \frac{\nu}{\nu_{M}} \sum_{z=1}^{Z} z \phi_{z}^{I}\right) + \psi^{II} e (1 - \gamma) \left(\phi_{+}^{II} - \phi_{\ell}^{II} + \frac{\nu}{\nu_{M}} \sum_{z=1}^{Z} z \phi_{z}^{II}\right)$$
(57)

Notice that we have weighted the electroneutrality conditions with with the elementary charge e and with the relative volume γ and $1 - \gamma$ occupied by phase I and II, respectively.

By differentiating L_2 with respect to ϕ_+^I and ϕ_l^I , we get

$$\frac{\partial f}{\partial \phi_{+}^{I}} + \lambda_{2} - \frac{\partial f}{\partial \phi_{\ell}^{I}} - \lambda_{1} + 2\psi^{I} = 0,$$
(58)

and similarly for phase II. Subtracting the expressions for the two phases and using (4)-(8) to evaluate the derivatives of f, we obtain

$$e\frac{\psi^{II} - \psi^{I}}{k_{B}T} = \frac{1}{2}\ln\left[\frac{\phi_{+}^{I}}{\phi_{\ell}^{I}}\frac{\phi_{\ell}^{II}}{\phi_{+}^{II}}\right],\tag{59}$$

The difference $\psi^{II} - \psi^{I}$ can be identified with the net potential jump due to the electric field between the two phases, also known as *Galvani potential* [37].

Returning to L_2 and setting its first derivatives with respect to the components of ϕ^I to zero, we obtain, after some algebra, the condition

$$\nu_M \left(\frac{\partial f}{\partial \phi_z^I} - \frac{\partial f}{\partial \phi_{z-1}^I} \right) = \nu \left(\frac{\partial f}{\partial \phi_+^I} - \frac{\partial f}{\partial \phi_s^I} \right), \tag{60}$$
$$z = 1 \dots Z + 1;$$

similarly for *I* replaced by *II*. This is exactly the condition (10), applied to each phase; see also (30). We therefore can use (14), together with (2), to eliminate the ϕ_z^I and ϕ_z^{II} variables, to get the minimisation problem

$$\gamma f(\phi_s^I, \phi_+^I, \phi_\ell^I, \phi_M^I) + (1 - \gamma) f(\phi_s^{II}, \phi_+^{II}, \phi_\ell^{II}, \phi_M^{II}) = \min!,$$
(61a)

subject to the constraints

$$\gamma \phi_{\ell}^{I} + (1 - \gamma) \phi_{\ell}^{II} = K_{1}^{0},$$
 (61b)

$$\gamma \phi_M^I + (1 - \gamma) \phi_M^{II} = K_5^0, \tag{61c}$$

$$\phi_s^R + \phi_+^R + \phi_\ell^R + \phi_M^R = 1, \quad R = I, \ II,$$
 (61d)

$$\phi_{+}^{R} - \phi_{\ell}^{R} + \frac{\nu}{\nu_{M}} \phi_{M}^{R} \mathcal{Q}^{R} = 0, \quad R = I, II,$$
(61e)

with constants K_1^0 and K_5^0 . Notice that (61c) replaces (56b) by a linear combination of the other constraints.

We treat this minimisation problem by using (61d) and (61e) to eliminate the ϕ_s^R and ϕ_+^R variables (for R = I, II) from f (and denote it by f^*) but including (61b) and (61c) via Lagrange multipliers. Differentiating with respect to ϕ_l^R , ϕ_M^R and γ gives the conditions

$$\mu_M^*(\phi_M^I, \phi_\ell^I) = \mu_M^*(\phi_M^{II}, \phi_\ell^{II}),$$
(62)

$$\mu_{\ell}^{*}(\phi_{M}^{I},\phi_{\ell}^{I}) = \mu_{\ell}^{*}(\phi_{M}^{II},\phi_{\ell}^{II}),$$
(63)

$$\mu_{M}^{*}(\phi_{M}^{I} - \phi_{M}^{II}) + \mu_{\ell}^{*}(\phi_{\ell}^{I} - \phi_{\ell}^{II}) = f^{*}(\phi_{M}^{I}, \phi_{\ell}^{I}) - f^{*}(\phi_{M}^{II}, \phi_{\ell}^{II}),$$
(64)

where

$$\mu_M^* = \partial f^* / \partial \phi_M \tag{65}$$

and

$$\mu_{\ell}^* = \partial f^* / \partial \phi_{\ell}, \tag{66}$$

These are the equations we solve using bifurcation packages as described in the main text; f^* is substituted by either f_{CR} (see (19)) or f_{FC} (see (25)) depending on the formulation of the model of interest.